


Material closed cellular polyurethane
Colour green

Standard dimensions on stock

thickness: 12.5 mm with Sylomer ND12
 25 mm with Sylomer ND25
 rolls: 1.5 m wide, 5.0 m long
 stripes: max. 1.5 m wide, up to 5.0 m long

other dimensions (also thickness), as well as stamped and molded parts on request

Standard Sylodyn range



Material properties	test methods	comment
tensile stress at break	2.5 N/mm ²	DIN EN ISO 527-3/5/100*
elongation at break	500 %	DIN EN ISO 527-3/5/100*
tear strength	10 N/mm	DIN 53515*
abrasion	100 mm ³	DIN 53516
coefficient of friction (steel)	0.7	Getzner Werkstoffe
coefficient of friction (concrete)	0.7	Getzner Werkstoffe
compression set	< 5 %	EN ISO 1856
static shear modulus	0.35 N/mm ²	DIN ISO 1827*
dynamic shear modulus	0.47 N/mm ²	DIN ISO 1827*
mechanical loss factor	0.08	DIN 53513*
rebound elasticity	70 %	DIN 53512
operating temperature	-30 up to 70 °C	depending on frequency, load and amplitude (reference value)
flammability	B2 B, C and D	DIN 4102 EN ISO 11925-2
specific volume resistance	> 10 ¹¹ Ω·cm	DIN IEC 93
thermal conductivity	0.09 W/[m·K]	DIN 52612/1

further characteristic values on request

* tests according to respective standards

** at form factor q=3

All information and data is based on our current knowledge. The data can be applied for calculations and as guidelines, are subject to typical manufacturing tolerances, and are not guaranteed.
 We reserve the right to amend the data.

Further information can be found in VDI Guideline 2062 - Page 2.

Getzner Werkstoffe GmbH
 Herrenau 5
 6706 Bürs
 Austria
 Phone +43-5552-201-0
 Fax +43-5552-201-899
 info.buers@getzner.com

Getzner Werkstoffe GmbH
 Am Borsigturm 11
 13507 Berlin
 Germany
 Phone +49-30-405034-00
 Fax +49-30-405034-35
 info.berlin@getzner.com

Getzner Werkstoffe GmbH
 Nördliche Münchner Str. 27a
 82031 Grünwald
 Germany
 Phone +49-89-693500-0
 Fax +49-89-693500-11
 info.gruenwald@getzner.com


Getzner Werkstoffe GmbH
 Middle East Regional Office
 Abdul-Hameed Sharaf Str. 114
 Rimawi Center - Shmeisani
 P.O. Box 961.303
 Amman 11996, Jordan
 Phone +962-560-7341
 Fax +962-569-7352
 info@geme.jo

Nihon Getzner K.K.
 Landmark Plaza, 8F
 Shiba Koen 1-67, Minato-ku
 105-0011 Tokyo, Japan
 Phone +81-3-5402-5340
 Fax +81-3-5402-6039

www.getzner.com


 the good vibrations company

full surface bearing




load deflection curve


form factor: $q=6$




strip bearing




form factor: $q=3$



point bearing



form factor: $q=1.5$




www.getzner.com

getzner
the good vibrations company

Quasi-static load deflection curve measured at a velocity of deformation of 1% of the thickness per second; testing between flat steel-plates; recording of the 3rd loading; testing at room temperature


modulus of elasticity

form factor: q=6




natural frequency


form factor: q=6




form factor: q=3




form factor: q=3



form factor: q=1.5




form factor: q=1.5



Static modulus of elasticity as a tangent modulus taken from the load deflection curve; dynamic modulus of elasticity due to sinusoidal excitation with a velocity level of 100 dBv re. $5 \cdot 10^{-8}$ m/s; test according to DIN 53513


Natural frequency of a single-degree-of-freedom system (SDOF system) consisting of a fixed mass and an elastic bearing consisting of Sylodyn® ND based on a stiff subgrade; parameter: thickness of elastomeric bearing

vibration isolation - efficiency




reduction of the transmitted mechanical vibrations by implementation of an elastic bearing consisting of Sylodyn® ND
parameter: factor of transmission in dB, isolation rate in %

creep behaviour





increase in deformation under consistent loading
parameter: permanent loading form factor: q=3

dynamic E-modulus at long term loading





change of dynamic modulus of elasticity under consistent loading (at 10 Hz)
parameter: load duration form factor: q=3

temperature dependency




DMA-test
(Dynamic Mechanical Analysis); tests within linear area of the load deflection curve, at low specific loads

frequency dependency




DMA-tests; mastercurve with a reference-temperature of 21°C, tests within the linear area of the load deflection curve, at low specific loads

dependency on amplitude



dependency on loading velocity



dependency on amplitude:
preload at static load limit;
form factor: q=3, thickness
of material 25 mm

**dependency on loading
velocity:**
form factor: q=3, thickness
of material 25 mm


Form factor

The form factor is a geometric measure for the shape of an elastomeric bearing defined as the ratio of the loaded area and the area of sum of the perimeter surfaces.

$$\text{definition: form factor} = \frac{\text{loaded area}}{\text{perimeter surface area}}$$

$$\text{for a rectangular shape: } q = \frac{l \cdot w}{2 \cdot t \cdot (l+w)}$$

(l..length, w..width, t..thickness)



The form factor has an influence on the deflection and the static load limit respectively.

Elastic Sylodyn-bearings are considered as


full surface bearing: form factor > 6

strip bearing: form factor between 2 and 6

point bearing: form factor < 2

Influence of the form factor on the deflection at the static load limit for a homogeneous material

reference value: form factor q=3



Influence of the form factor on the static load limit for a homogeneous material

reference value: form factor q=3

